

Brilliant General Purpose Fluorescent Pigments

BGP SERIES

A tinctorially strong general purpose fluorescent pigment for use in low polarity systems including paper coatings, paints, screen inks, plastisols and gravure Type "A" inks.

Principal Applications

- Paper Coatings
- Flexo and Gravure Inks
- Screen and Textile Inks
- Garment Dyeing
- Aqueous and Non-aqueous Systems
- Brush-on, and Spray Paints
- Plastisols
- Coatings

Product Features and Benefits

- High Color Strength Extra strength pigments offer formula flexibility and increased value in use
- A complete palette of fluorescent colors Provides a wide range of color options
- Broad compatibility Formulations can be prepared in a wide range of media

Pigment Specifications

Particle size ¹	3-5 microns
Hegman Grind	Approx. 5.5
Softening Point	Approx. 165-205°F
Decomposition Temp.	570°F to 580°F
Specific Gravity ²	1.3
Bulking value (gallons/pounds)	0.0856

¹ By laser diffraction

² Represents specific gravity of the solid pigment; This should not be used to determine the pounds per gallon of the pigment powder

Solubility³ and Bleed Resistance^{4,5}

	<u>Solubility</u>	<u>Bleed</u>
Aliphatic Hydrocarbons	A	1
Aromatic Hydrocarbons	A-C	1-4
Alcohols - low polarity	A-C	2
Alcohols - high polarity	C-D	4
Ketones - low polarity	B-C	3
Ketones - high polarity	C-D	4
Esters - low polarity	A-C	1-2
Esters - high polarity	C-D	2-4
Glycols	A-B	1-2
Glycol Ethers	C-D	3-4
Chlorinated Solvents - low polarity	A-B	1-2
Chlorinated Solvents - high polarity	C-D	3-4
Plasticizers	A-D	1-4

Note: Combinations of different solvents may give different results and should be tested.

A - Insoluble 1 - None
 B - Slightly Soluble 2 - Slight
 C - Partly Soluble 3 - Moderate
 D - Soluble 4 - Considerable

³Test conditions, Water bath, 30 minutes, 100°F

⁴Following solubility test, appearance of the supernatant liquid is observed

⁵Green and Blue fluorescent pigments generally exhibit superior bleed resistance

Color Guide

<u>SHADE</u>	<u>CODE</u>
Pink	BGP-PK111
Cerise	BGP-CE112
Red	BGP-RD113
Orange-Red	BGP-OR114
Orange	BGP-OG115
Orange-Yellow	BGP-OY116



Yellow	BGP-YE117
Green	BGP-GR118
Blue	BGP-BL119
Violet	BGP-VT120
Violet	BGP-VT120-2
Magenta	BGP-MG121

Storage: When stored in a cool, dry environment, BGP pigments have an indefinite shelf life. Colorant containers should be kept closed to minimize contamination.

Toxicity: Tests conducted through independent laboratories have found Brilliant Group BGP Series Fluorescent Pigments to be "essentially non-toxic." A summary of the test data is listed on the MSDS, which is available upon request. Good industrial hygiene and handling methods are essential in the use of all products whether or not they are determined to be hazardous.

Important

Brilliant Group makes no warranty, whether expressed or implied, including warranties of merchantability or of fitness for a particular purpose of this product. No statements or recommendations contained in the product brochure are to be construed as inducements to infringe any relevant patent, now or hereafter in existence. Under no circumstances shall Brilliant Group be liable for incidental, consequential or other damages from alleged negligence, breach of warranty, strict liability or any other theory, arising out of the use or handling of this product.